

CONTACT WITH: JACKY CHEN MOBILE: 13670242510

Specification for Magnetic Transducer		Page (页)	2/11
Model No (型号) .: LIR2430			
CONTENTS <u>1. 適用範圍</u> Applicable Scope <u>2. 產品類型</u> Type of Products <u>3. 主要特點</u> General Features <u>4. 規格特性表</u> Spec Chart <u>5. 電池特性</u> Battery Characteristics <u>6. 注意事項</u> Important Notes			

Specification for Magnetic Transducer		Page (页)	3/11
Model No (型号) .: LIR2430			
1. 適用範圍 Applicable Scope 本承認書適用於邁洛克電池生產的鋰離子充電電池。 This specs approval is applied only for the lithium-ion rechargeable cell battery produced by MALAK. 2. 產品類型 Type of Products 種類: 扣式鋰離子充電電池 Type : Lithium-ion rechargeable cell battery 型號: LIR2430 Model : LIR2430 3. 主要特點 General Features 使用壽命長 Long Cycle Life 正常使用條件下，可迴圈使用充放電周期≥ 500周，容量$\geq 80\%$。 Under normal usage, the cycle life of the battery can be ≥ 500 circles while with capacity $\geq 80\%$ 比能量大 High Power Density 高能量密度，使電池重量輕、體積小，更使用於小型用電設備。 High power density makes the battery light in weight and small in dimension. It can be used in small devices. 使用安全可靠 Safe and Reliable 沒有遊離的金屬鋰，電池使用更安全。 No floating metal lithium assures a safer usage. 工作電壓高 High working voltage 工作電壓高達 3.6V，大約是鎳鎘或鎳氫電池的 3 倍，可減小電池的使用數量。 Working voltage is up to 3.6V, approx. 3 times of the voltage of NI-MH or NI-CD, which reduces the quantity of the battery needed in certain application. 無記憶效應 No memory effect 無記憶效應，使其無時不為你提供最大的能量。 No memory effect assures a constant maximum application. 自放電率小$\leq 7\%$/月。 Low self-discharge rate : $\leq 7\%$/month 一致性好 Good Consistency 公司內部按 ISO9000 標準建立質量保證體系，對生產全過程實行嚴格控制，使電池容量、內阻、放電平臺、荷電保持能力等性能保持良好的一致性。 Good consistency is showed in battery capacity, internal resistance, discharge platform and capacity retention. A strict complete internal quality control is subject to the ISO9000 system in the company's production.			

Specification for Magnetic Transducer			Page (页)	4/11
Model No (型号) .: LIR2430				
4.规格特性表 Spec Chart				
项目		标准特性		
型号		LIR2430		
额定电压 (V)		3.6		
标称容量 (mAh)		70±5		
内阻 (mΩ)		≤500		
尺寸	直径 (mm)	24.5 -0.2		
	高度 (mm)	3.0 +0.3		
重量 (g)		3.8		

内阻值检测标准：以 0.5CmA 恒流充电，当电池端电压达到充电限制电压 4.25V 后，转为恒压充电，当电流值小于 0.05CmA 时终止充电并搁置 1 小时后，用 1000Hz 内阻仪器进行检测。

Internal resistance test standard:
CC charge 0.5mA / voltage up to 4.25V; Then CV charge.
Terminate charging when the charging current value is less than 0.05CmA.
Rest for 60 minutes, then test the battery by 1000Hz internal resistance tester.

5. 電池特性 Battery Characteristics

5.1 測試條件 Test Conditions

Temperature 溫度：20℃±1

Relative Humidity: 相對濕度：≤75%±5

Atmosphere pressure 大氣壓力：1atm

5.2 放電特性 Discharge Characteristics

在上述條件下測試：The test should be conducted under the condition below:

在環境溫度 20±5℃的條件下，以 0.5CmA 恒流充電，當電池端電壓達到充電限制電壓 4.25V 後，轉為恒壓充電，當電流值小於 0.05CmA 時終止充電並放置不超過 1 小時，再以 0.5CmA 電流恒流放電到 2.75V

In a temperature of 20±5℃, CC charge 0.5CmA / voltage up to 4.25V; Then CV charge.

Terminate charging when the charging current value is less than 0.05CmA.

Rest for no more than 60 minutes,

Discharge CC at 0.5CmA to 2.75V.

5.3 充電特性 Charge Characteristics

電池可採用下列方法之一進行充電：The battery can be charged by one of the following methods:

標準充電：在環境溫度 20±1℃的條件下，以 0.5CmA 恒流充電，當電池端電壓達到充電限制電壓 4.25V 時，改為恒壓充電，直到充電電流小於 0.05CmA，停止充電。

Standard Charge : Temperature 20±1℃, CC charge at 0.5CmA to 4.25V; turn to CV charge; Terminate charging when the charging current value is less than 0.05CmA.


快速充電：在環境溫度 20±5℃的條件下，以 1CmA 恒流充電，當電池端電壓達到充電限制電壓 4.25V 時，改為恒壓充電，直到充電電流小於 0.05CmA，停止充電。

Fast Charge: Temperature 20±5℃, CC charge at 1.0CmA to 4.25V; turn to CV charge; Terminate charging when the charging current value is less than 0.05CmA.

Specification for Magnetic Transducer		Page (页)	5/11
Model No (型号) .: LIR2430			
充放電曲線請參閱圖 1 和圖 2 ; For charging/discharging characteristics at various currents see fig 1 or 2. 不同溫度放電曲線請參閱圖 3 ; For discharging characteristics at various temperatures see fig 3 or 4. 自放電曲線請參閱圖 4 ; For Storage characteristics see fig 4. 迴圈壽命曲線請參閱圖 5 。 For cycle life characteristics see fig 5.			

Specification for Magnetic Transducer	Page (页)	6/11
Model No (型号) .: LIR2430		


圖 1. 不同電流條件下的充電特性
Fig.1 Charging Characteristics at various currents



Specification for Magnetic Transducer	Page (页)	7/11
Model No (型号) .: LIR2430		


圖 2. 不同電流條件下的放電特性

Fig. 2 Discharge Characteristics at various currents




Specification for Magnetic Transducer	Page (页)	8/11
Model No (型号) .: LIR2430		

圖 3. 不同溫度條件下的放電特性
Fig. 3 Discharging Characteristics at various Temperatures




Specification for Magnetic Transducer	Page (页)	9/11
Model No (型号) .: LIR2430		

圖 4. 自放電保持特性
Fig. 4 Storage Characteristics



Specification for Magnetic Transducer	Page (页)	10/11
Model No (型号) .: LIR2430		

圖 5. 迴圈壽命曲線
Fig. 5 Cycle Life Chart



Specification for Magnetic Transducer	Page (页)	11/11
Model No (型号) .: LIR2430		

6.注意事項 Important Notes

遠離熱源、火源；Keep away from source of fire and/or heat.

不要擅自解剖電池或電池組；Do not disassemble battery and/or battery pack.

不要將電池的正負極用金屬片連接，也不要將電池與能夠引起其短路的物品一起混放；
Do not connect the positive and negative pole directly using conductive metal;
avoid short circuit.

不要將電池投入水中或弄濕； Do not put the battery into water or damp it.

不得拋電池；Do not cut the battery.

不得針刺、打擊電池；Do not strike or needle the battery.

用專用的充電器進行充電；Charge the battery using specified chargers.

不要用錫焊直接焊接引線與電池連接；Do not solder the battery directly.

不要反接電池的正負極；Observe the correct polarity (+/-)

不要將電池用於未指定的應用領域；Do not use the battery in un-specified application.

不得將電池與乾電池或其他類型電池混用；Do not mix the battery in usage with other types of battery.

使用電池前應該仔細閱讀使用說明書. Read the instruction manual carefully before use.